

517595

(19) World Intellectual Property Organization
International Bureau



13 DEC 2004



(43) International Publication Date
24 December 2003 (24.12.2003)

PCT

(10) International Publication Number
WO 03/106171 A1

- (51) International Patent Classification⁷: **B32B 27/34**, 27/32, C08G 69/08, 69/16, 69/48
- (21) International Application Number: PCT/NL03/00379
- (22) International Filing Date: 21 May 2003 (21.05.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
1020830 12 June 2002 (12.06.2002) NL
- (71) Applicant (for all designated States except US): **DSM IP ASSETS B.V.** [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **DE KROON, Jan** [NL/NL]; In de Neerakker 1A, NL-6093 JH Heythuysen (NL). **BRINK, Ted** [NL/NL]; Charles Voscour 4, NL-6211 XR Maastricht (NL).
- (74) Agent: **KRIJGSMAN, Willem**; DSM Patents & Trade-marks, P.O. Box 9, NL-6160 MA Geleen (NL).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR PRODUCING A MULTILAYER FLAT FILM CONTAINING AN INTRINSICALLY GEL-FREE, RANDOMLY BRANCHED POLYAMIDE

(57) Abstract: Process for producing a multilayer flat film containing a polyamide layer and a layer of another polymer wherein the polyamide layer is essentially formed from an intrinsically gel-free, randomly branched polyamides at least composed of units derived from: a. AB monomers, which are understood to be a monomer possessing both a carboxylic acid group (A) and an amine group (B), b. at least one compound I, being a carboxylic acid (A_v), with functionality v ≥ 2 or an amine (B_w) with functionality w ≥ 2, c. at least one compound II, being a carboxylic acid (A_v) with functionality v ≥ 3 or an amine (B_w) with functionality w ≥ 3, with compound II being a carboxylic acid if compound I is an amine is or with compound II being an amine if compound I is a carboxylic acid, in specific quantities. The other polymer preferably is polyethylene and more preferably a non-linear polyethylene. Preferably, the polyamide layer and the layer of the other polymer are adjacent to each other.

WO 03/106171 A1

PROCESS FOR PRODUCING A MULTILAYER FLAT FILM CONTAINING A POLYAMIDE

5

The invention relates to a process for producing a multilayer flat film containing a polyamide layer and a layer of another polymer.

The art of producing multilayer flat film and the problems that may arise therein are described in the publication "Effects of flow instability in co-extruded films",
10 Tappi Journal 1992, pages 205-211. One of the most important problems mentioned therein is the occurrence of deviations in the thickness distribution of the various layers at the edge of the multilayer film. As a solution to this problem it is suggested to modify the shape of the die for one of the layers so as to compensate for the occurrence of the thickness differences. This approach has the drawback that the processing window, which
15 should be taken to mean the set of machine settings at which the film can be produced, becomes very narrow. For example, the output speed and thus production rate are limited and must be maintained within narrow limits, because the extent to which the undesired side effect occurs is dependent on the output speed and thus the required modification of the die is also dependent on that speed. Another suggested solution is to provide a
20 temperature profile in the dies. This solution has the same drawbacks as those mentioned earlier. It is also suggested to align the molecular weights of the various materials. It will be clear that this will change certain material properties and thus also the properties of the flat film formed. Thus, in many cases a film having the desired properties will not be obtained.

Polyamide is a material that is commonly applied in multilayer films, and
25 the problem described arises also when polyamide is applied. As a rule, the polyamide layer is intended to impart barrier properties to the film, whilst the layer of the other polymer imparts another property to the film, for example water-tightness, tear strength or a good gloss.

The invention aims to provide a process for producing a multilayer flat
30 film containing, besides a polyamide layer, also at least another polymer and that can be applied in a wide processing window without any modification being required for a die.

This aim is achieved according to invention by the polyamide layer being essentially formed from randomly branched polyamides at least composed of units derived from:

- a. AB monomers, which are understood to be a monomer possessing both a carboxylic acid group (A) and an amine group (B),
- b. at least one compound I, being a carboxylic acid (A_v) with functionality $v \geq 2$ or an amine (B_w) with functionality $w \geq 2$,
- 5 c. at least one compound II, being a carboxylic acid (A_v) with functionality $v \geq 3$ or an amine (B_w) with functionality $w \geq 3$, with compound II being a carboxylic acid if compound I is an amine is or with compound II being an amine if compound I is a carboxylic acid, wherein the amounts of units derived from all carboxylic acids and amines in the polyamide satisfy formula 1

10

$$P < 1 / [(F_A - 1) \cdot (F_B - 1)] \quad (1)$$

where:

15

$$P = [\Sigma(n_i \cdot f_i)]_X / [\Sigma(n_i \cdot f_i)]_Y \quad (2)$$

where $P \leq 1$ and either $X = A$ and $Y = B$ or $X = B$ and $Y = A$ and

20

$$F = \Sigma (n_i \cdot f_i^2) / \Sigma (n_i \cdot f_i) \quad (3)$$

for, respectively, all carboxylic acids (F_A) and amines (F_B), wherein f_i is the functionality of a carboxylic acid (v_i) or amine (w_i), n_i is the number of moles of a carboxylic acid or amine and the summation is conducted for all units derived from carboxylic acids and amines in the polyamide.

25

These give films with a highly uniform appearance, without the irregularities caused by gels. The specified branched polyamides are known from WO-00/35992 and the definitions given there for the various components in the above formula apply here also. In particular compound I and compound II are also understood to be mixtures of several carboxylic acids having the same functionality or mixtures of several

30 amines having the same functionality.

In most cases, when the specified branched polyamide is used as a polyamide layer in the production of multilayer flat film, the occurrence of the undesired

side effects proves to be prevented also when the customary rectangular dies are used. It is thus possible to produce multilayer flat film in a stable manner and at high speeds in a wide processing window without any modification of dies.

This favourable effect occurs in particular when polyethylene is used as the other polymer and more in particular when the polyethylene is a non-linear polyethylene. The production of multilayer flat film is a technology known per se, usually employing the co-extrusion technique. Here, the materials for the various layers are melted in separate extruders and transported to an extruder head equipped with one or more outflow openings. The various molten streams are then in molten condition contacted with each other across the desired width. This can be effected by for example positioning the dies, from which the various materials emerge, one directly above the other or in parallel or by contacting the various materials with each other already in the head and expelling the formed multilayer product through a common die. The formed, molten multilayer film is then cooled and rolled. The process according to invention may employ the known techniques of making multilayer flat films.

Highly suited for application in the process according to the invention is branched polyamide wherein caprolactam is the predominant monomer unit. The branched polyamide may contain minor amounts of a non-branched, linear polyamide, for example up to 10 wt.%. The polyamide may also contain the customary additives, for example grafting agents, lubricants, antistatics, anti-blocking agents, colorants and stabilizers. The latter equally applies to the layer of another polymer to be discussed below.

The polyamide consists essentially of branched polyamide, which means that, besides the branched polyamide, an amount of non-branched polyamide may also be present. This amount should be so limited that the favourable effects of the use of the branched polyamide are not lost to an unacceptable extent. Preferably at least 50% of the polyamide in the polyamide layer is branched polyamide and more preferably at least 75 % and even 90%. The favourable effect of the presence of the branched polyamide is most manifest when all polyamide in the layer is branched polyamide. Mixtures of different branched polyamides may also be used as branched polyamide.

Suitable materials for the other polymer layer in the process according to invention are all film-forming polymers, in particular the branched forms thereof. Especially suitable as a material for another polymer layer is polyethylene. Examples of suitable

ethylene polymers are all thermoplastic homopolymers, producible with the known catalysts such as Ziegler-Natta, Phillips and metallocene catalysts, of ethylene and copolymers of ethylene having as comonomer one or more α -olefins with 3-10 C atoms, in particular propylene, isobutene, 1-butene, 1-hexene, 4-methyl-1-pentene and 1-octene.

5 The amount of comonomer normally is between 0 and 50 wt.%, preferably between 5 and 35 wt.%. Such polyethylenes are also known as for example high-density polyethylene (HDPE), low-density polyethylene (LDPE), linear low-density polyethylene (LLDPE) and linear very low density polyethylene (VL(L)DPE). Non-linear ethylene polymers are preferred. In addition, branched polypropylene with a Melt Flow Index preferably between
10 0.5 and 5 g/10 min is highly suitable as a material for the other polymer layer. Suitable polyethylenes have a density of between 860 and 970 kg/m³.

The advantages of the process according to invention, in particular as regards the width of the processing window, become particularly manifest when non-linear polyethylene is used as other polymer. Examples hereof are the LDPE and HDPE
15 described above.

As a rule, in the process according to the invention the polyamide layer preferably is adjacent to the layer of the other polymer. Application of the polyamide layer and the layer of the other polymer as adjacent functional layers directly connected to each other or connected by an adhesive layer has been found to yield a flat film of highly
20 uniform thickness also at the edges of the film. The layers may thus be directly adjacent to each other but an adhesive layer may also be present between the layers. Adhesive layers between the polyamide and the other polymer are also applied according to the state of the art and thus are known per se. Such known adhesive layers may also be applied in the process according to the invention. The same applies to materials that can be admixed in
25 the other polymer in order to promote adhesion to the polyamide layer. If polyethylene is used as polymer for the other layer, suitable materials for an adhesive layer are for example modified polyolefins, such as LDPE, LLDPE, metallocene PE, polyethylene-vinyl alcohol, polyethylene-acrylic acid, polyethylene-methacrylic acid and polypropylene, that are grafted with at least a compound chosen from the group of α,β -unsaturated
30 dicarboxylic acids, for example maleic acid, fumaric acid and itaconic acid and anhydrides, acidic esters, acidic imides and acidic imines thereof. Modified copolymers of ethylene and the aforementioned dicarboxylic acids may also be applied as adhesive layer in the

manner indicated.

If the layers are directly adjacent to each other, the layer of the other polymer preferably consists of a mixture of that polymer and a material described above as being suitable as an adhesive layer in order to promote adhesion between the layer of the other polymer and the polyamide. In case polyethylene is the other polymer the
5 aforementioned modified polyolefin preferably is present in the mixture as adhesion promoter.

The polyamide layer may also be adjacent to a layer of the other polymer on two sides, for example an LDPE layer, and the other way round. The formed film then
10 has for example a PA-LDPE-PA or LDPE-PA-LDPE sandwich structure.

Besides the mentioned layers, one or more other functional layers may also be placed over the polyamide layer or the layer of the other polymer, it being preferred for the the polyamide layer and the layer of the other polymer to be adjacent to each other. Other layers often used in multilayer flat film are those which consist of for
15 example ethylene-vinylalcohol and ionomers.

The total thickness of multilayer films that are produced in practice as multilayer flat film and are also produced by the process according to the invention is between 20 and 300 μm . In the process according to the invention the layer of the other polymer, for example the polyethylene layer in the multilayer flat film, preferably has a
20 thickness of at least 10 μm . The upper limit of the thickness is given by the intended application and the properties required therefor and extends in practice to approx. 100 μm . The branched-polyamide layer has a thickness of at least 2 μm and preferably of at least 20% of the thickness of the polyolefin layer, up to a maximum of 150, preferably 100 μm . Any other layers present have such thicknesses that they are able to perform their
25 intended function during the production process or in the multilayer flat film to be formed.

The production rates applied in the process according to invention prove to be able to be chosen higher than when the conventional non-branched polyamide is used. Rates up to a factor of 2 or even 4 higher than when non-branched polyamide is used have proved possible in the process according to invention, which thus has a
30 markedly larger operating window than the known process.

The invention further relates to a multilayer flat film containing a polyamide layer and a layer of another polymer, wherein the polyamide layer is essentially

formed from an intrinsically gel-free, randomly branched polyamides as defined hereinbefore. This multilayer film combines a high degree of smoothness and is gelfree.

The invention will be elucidated with reference to the following examples and comparative experiments.

5

Experimental set-up and procedure

A five-layer flat film made up of 30 μm polyethylene/5 μm adhesive layer/30 μm polyamide/5 μm adhesive layer/30 μm polyethylene was produced. As polyethylene use was made of an LDPE with a Melt Flow Index of 4.4 g/10 min, as
10 adhesive layer Yparex™ 0H042, an MZA-modified LLDPE. As non-branched nylon use was made of Akulon F 132-E (relative viscosity 3.2), as branched polyamide a polyamide made from 97 parts by weight of caprolactam, 0.62 part by weight of bis-hexamethylene-triamine, 0.42 part by weight of adipic acid and 0.71 part by weight of benzoic acid with a relative viscosity in formic acid of 2.80, as polymer. This polymer was post-condensed in
15 the solid phase to a relative viscosity of 2.95 and provided with grafting agent and lubricant.

The film was produced in an extrusion line equipped with a single 60 mm extruder for melting and extruding the polyamide and with two 45 mm extruders for melting polyethylene and the adhesive layer, respectively. In the extruders an ascending
20 temperature profile was maintained, ascending for the nylon from 215 to 280°C, ascending for the polyethylene from 170 to 230°C and ascending for the adhesive layer from 170 to 210°C. The outlet of the extruders was connected to a black box wherein the molten polymers were supplied in the indicated layer configuration to a die having five parallel, rectangular slits approx. 125 cm wide. The die temperature was 280-290°C.

25

Comparative Experiment A

A five-layer film was produced in the manner described above at a production rate of 7.5 m/min and with a width of 115 cm. The non-branched polyamide was used as polyamide. Virtually no polyamide proved to be present over a distance of
30 approx. 13 cm on both sides of the film.

Examples I-III

Comparative Experiment A was repeated except that the branched polyamide was used as polyamide. The production was successively set to 7,5, 15 and 30 m/min. The polyamide in the produced proved to be present across virtually the full width of the film.

Comparative Experiment B

The example with the production rate of 30 m/min was repeated with the non-branched polyamide under the same conditions as the branched polyamide. The stability of the process diminished and no polyamide proved to be present along the edges over a width of 13 cm.

CLAIMS

1. Process for producing a multilayer flat film containing a polyamide layer and a layer of another polymer, characterized in that the polyamide layer is essentially
 5 formed from an intrinsically gel-free, randomly branched polyamides at least composed of units derived from:
- a. AB monomers, which are understood to be a monomer possessing both a carboxylic acid group (A) and an amine group (B),
 - b. at least one compound I, being a carboxylic acid (A_v) with functionality $v \geq 2$ or an amine (B_w) with functionality $w \geq 2$,
 - 10 c. at least one compound II, being a carboxylic acid (A_v) with functionality $v \geq 3$ or an amine (B_w) with functionality $w \geq 3$, with compound II being a carboxylic acid if compound I is an amine or with compound II being an amine if compound I is a carboxylic acid, wherein the amounts of units derived from all carboxylic acids and amines in the polyamide satisfy formula 1

$$P < 1 / [(F_A - 1) \cdot (F_B - 1)] \quad (1)$$

where:

$$P = [\sum (n_i \cdot f_i)]_X / [\sum (n_i \cdot f_i)]_Y \quad (2)$$

where $P \leq 1$ and either $X = A$ and $Y = B$ or $X = B$ and $Y = A$ and

$$F = \sum (n_i \cdot f_i^2) / \sum (n_i \cdot f_i) \quad (3)$$

for, respectively, all carboxylic acids (F_A) and amines (F_B), wherein f_i is the functionality of a carboxylic acid (v_i) or amine (w_i), n_i is the number of moles of a carboxylic acid or amine and the summation is conducted for all units derived from carboxylic acids and amines in the polyamide.

- 2. Process according to claim 1 wherein the other polymer is polyethylene.
- 3. Process according to claim 2 wherein the polyethylene is a non-linear

polyethylene.

4. Process according to any one of claims 1-3 wherein the polyamide layer and the layer of the other polymer are adjacent to each other.

5. Multilayer flat film containing a polyamide layer and a layer of another polymer, characterized in that the polyamide layer is essentially formed from an intrinsically gel-free, randomly branched polyamides at least composed of units derived from:

a. AB monomers, which are understood to be a monomer possessing both a carboxylic acid group (A) and an amine group (B),

b. at least one compound I, being a carboxylic acid (A_v) with functionality $v \geq 2$ or an amine (B_w) with functionality $w \geq 2$,

c. at least one compound II, being a carboxylic acid (A_v) with functionality $v \geq 3$ or an amine (B_w) with functionality $w \geq 3$, with compound II being a carboxylic acid if compound I is an amine or with compound II being an amine if compound I is a carboxylic acid, wherein the amounts of units derived from all carboxylic acids and amines in the polyamide satisfy formula 1

$$P < 1 / [(F_A - 1) \cdot (F_B - 1)] \quad (1)$$

where:

$$P = [\sum (n_i \cdot f_i)]_X / [\sum (n_i \cdot f_i)]_Y \quad (2)$$

where $P \leq 1$ and either $X = A$ and $Y = B$ or $X = B$ and $Y = A$ and

$$F = \sum (n_i \cdot f_i^2) / \sum (n_i \cdot f_i) \quad (3)$$

for, respectively, all carboxylic acids (F_A) and amines (F_B), wherein f_i is the functionality of a carboxylic acid (v_i) or amine (w_i), n_i is the number of moles of a carboxylic acid or amine and the summation is conducted for all units derived from carboxylic acids and amines in the polyamide.

INTERNATIONAL SEARCH REPORT

PCT/NL 03/00379

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B32B27/34 B32B27/32 C08G69/08 C08G69/16 C08G69/48

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B32B C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 000 363 A (BASF AG) 24 January 1979 (1979-01-24) page 4 page 6; claims; examples	1-8
A	WO 00 35992 A (ABERSON RENE ;DSM NV (NL); NIJENHUIS ATZE JAN (NL); SCHOLTENS BOUD) 22 June 2000 (2000-06-22) cited in the application claims; examples I-VIII; table 2	1-8
A	WO 02 12371 A (RHODIA ENGINEERING PLASTICS S ;SILVESTRO GIUSEPPE DI (IT); ZHANG H) 14 February 2002 (2002-02-14) claims	1-8
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

11 September 2003

Date of mailing of the international search report

22/09/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Ibarrola Torres, 0

INTERNATIONAL SEARCH REPORT

PCT/NL 03/00379

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 99 03909 A (SILVESTRO GIUSEPPE DI ;GUAITA CESARE (IT); ZHANG HAICHUN (IT); NYL) 28 January 1999 (1999-01-28) page 4; claims -----	1-8
A	US 6 355 358 B1 (BOEER MICHAEL ET AL) 12 March 2002 (2002-03-12) the whole document -----	1-8

INTERNATIONAL SEARCH REPORT

Information on patent family members

PCT/NL 03/00379

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0000363	A	24-01-1979	DE 2732329 A1	01-02-1979
			DK 315778 A	17-01-1979
			EP 0000363 A1	24-01-1979
			IT 1105250 B	28-10-1985
			JP 54020096 A	15-02-1979
WO 0035992	A	22-06-2000	NL 1010819 C2	19-06-2000
			AT 224925 T	15-10-2002
			AU 1697600 A	03-07-2000
			CN 1334839 T	06-02-2002
			DE 69903197 D1	31-10-2002
			DE 69903197 T2	12-06-2003
			EP 1159336 A1	05-12-2001
			JP 2002532594 T	02-10-2002
			WO 0035992 A1	22-06-2000
			US 2002022712 A1	21-02-2002
WO 0212371	A	14-02-2002	FR 2812880 A1	15-02-2002
			AU 8398701 A	18-02-2002
			BR 0113252 A	24-06-2003
			CA 2418838 A1	14-02-2002
			WO 0212371 A1	14-02-2002
			EP 1313793 A1	28-05-2003
WO 9903909	A	28-01-1999	FR 2766197 A1	22-01-1999
			AU 8629798 A	10-02-1999
			BR 9810722 A	08-08-2000
			CN 1264397 T	23-08-2000
			WO 9903909 A1	28-01-1999
			EP 0996659 A1	03-05-2000
			JP 2001510216 T	31-07-2001
			PL 338122 A1	25-09-2000
US 6355358	B1	12-03-2002	DE 10005641 A1	04-01-2001
			BR 0002904 A	30-01-2001
			CA 2312582 A1	29-12-2000
			CN 1290601 A	11-04-2001
			EP 1065048 A2	03-01-2001
			JP 2001071436 A	21-03-2001